



SCHEDA TECNICA - DATA SHEET INDURITORE 302

GENERAL DESCRIPTION:

It is a special aliphatic polyisocyanate catalyst for PVA adhesives.

APPLICATIONS

It is used to increase water resistance of PVA glues for the compliance with the DIN standard EN204-205 group D4.

If it used in polyurethane dispersions, as Nunipur, it increase the heat resistance of the final product.

CHARACTERISTICS

| | | |
|---|--------------------|-------|
| FORM | liquid | |
| COLOUR | slightly yellowish | |
| Brookfield's viscosity a 23°C | 950 - 1550 | mPa·s |
| POT LIFE for PVA dispersions at 23°C | 4 - 6 | hours |
| POT LIFE for Nunipur polyurethane dispersions at 23°C | 6 - 8 | hours |

WARNING

During work do not exceed the pot life of the mixture. When it happens and the reaction is completed, a blowing up appears

PACKAGING

Plastic bottle of 0,5kg;

Box with 25 plastic bottles of 0,5 kg;

STORAGE

Shelf life: 6 months at 20°C in original closed packages.

Storing the product at a temperature higher than 30°C may cause an alteration of it.

STORAGE TEMPERATURE NOT BELOW 10°C.

The above data are the results of our experiences and they have to be considered as suggestions, due to the variety of the working conditions.

Date: November '14;

version n° 05

- THIS TECHNICAL SHEET HAS NOT TO BE CONSIDERED AS A PRODUCT SPECIFICATION -